

A better environment inside and out.™

Solar Gard® Solar Control Window Films

# Sterling 70


Performance results	1/8" (3mm)	1/4" (6mm)	1/8" + 1/8" (3mm+3mm)
Solar energy			
% Transmittance	61	55	52
% Absorptance	22	31	29
% Reflectance	17	14	20
Visible light			
% Transmittance	75	74	68
% Reflectance exterior	13	13	19
% Reflectance interior	12	12	17
Emissivity	.80	.80	.80
Winter U-Factor (W/m <sup>2</sup> C)	5.79	5.71	2.70
Shading coefficient	.77	.74	.74
Solar heat gain coefficient	.67	.64	.64
Solar selectivity index – luminous efficacy (VLT/SC)	.97	1.00	.92
Light to solar heat gain factor (VLT/SHGC)	1.12	1.16	1.06
% Ultraviolet light blocked @ 300 to 380 nm	>99	>99	>99
% Total solar energy rejected	33	36	36
% Summer solar heat gain reduction	23	22	16
% Glare reduction	17	17	17

## Physical properties nominal

Gauge	2.0 mil (50 micron)
Tensile strength	30,000 lbs/in <sup>2</sup> (2,110 kg/cm <sup>2</sup> )

## Film Performance

Performance results were generated from testing 1/8" (3mm) thick clear glass.



All performance results are based on the film installed on the inside surface of 1/8" (3mm), 1/4" (6mm), and 1/8" + 1/8" (3mm+3mm) thick, clear glass.

[www.solargard.com.au](http://www.solargard.com.au)

SK0314ST7AU 02/12  
 © Copyright 2012, Saint-Gobain Performance Plastics Corporation and/or its affiliates  
 All Rights Reserved • [www.solargard.com](http://www.solargard.com)

Please recycle



### Notes

- Solar Gard is a participating member of AIMCAL (the Association of Industrial Metallizers, Coaters and Laminators), IWFA, and EWFA. Performance results are calculated using NFRC methodology and LBNL Window 5.2 software, and are subject to variations within industry standards and only intended for estimating purposes.
- These test data contain only results arrived at after employing specific test procedures and standards. The included data do not constitute a recommendation for, endorsement of, or certification of the product or material tested. These data are provided for informational purposes only and are not to be considered part of the basic representation or warranty, expressed or implied, including the implied warranties of merchantability or fitness for a particular purpose, that its products will conform to these test data. Solar Gard's limited warranty should be carefully reviewed prior to purchasing any Solar Gard product. Extrapolation of data from the sample or samples relation to the batch or lot from which data were obtained may not correlate and should be interpreted accordingly with caution. Solar Gard shall not be responsible for variations in quality, composition, appearance, performance, or other feature of similar subject matter produced by persons or under conditions over which Solar Gard has no control.
- Performance results for summer solar heat gain reduction and glare reduction are calculated by comparing filmed glass to that of untreated glazing.

