

Commercial Solutions Division

# 3M™ Thinsulate™ Window Film CC75

## Climate Control Window Film

### Product Bulletin

## 1. Product Description

3M™ Thinsulate™ Window Film Climate Control 75 is a combined solar control and insulating window film for interior applications.

## 2. Applications

3M™ Thinsulate™ Window Film Climate Control 75 is intended for interior application on flat glass substrates.

## 3. Typical Properties

These are indicative values for 3M™ Window Film products.

Product construction	
Material base	Metallized Polyester
Adhesive	Pressure sensitive acrylic
Protective liner	Siliconized PET

Typical Performance Properties according to EN 410												
Glass Type	Film Type	Visible Light			Total Solar Energy Rejected	G Value (SHGC)	LSG (Light to solar gain)	U Value		Heat Loss Reduction	Heat Gain Reduction	Glare Reduction
		Reflected (interior)	Reflected (exterior)	Transmission				btu/hft²F	W/m²K			
Single Pane												
Clear	No Film	9	8	89	19	0.82	1.1	1.03	5.9	NA	NA	NA
	TCC 75	12	16	74	47	0.53	1.4	0.62	3.6	40	35	17
Tinted	No Film	6	6	53	37	0.63	0.8	1.03	5.9	NA	NA	NA
	TCC 75	10	8	44	60	0.4	1.1	0.62	3.6	40	37	17
Double Pane												
Clear	No Film	15	15	79	30	0.7	1.1	0.47	2.6	NA	NA	NA
	TCC 75	17	21	66	49	0.51	1.3	0.36	2.0	26	27	16
Tinted	No Film	13	8	47	49	0.51	0.9	0.47	2.6	NA	NA	NA
	TCC 75	15	10	40	63	0.37	1.1	0.35	2.0	26	27	15

The values above are the results of illustrative lab test measurements and shall not be considered as a commitment from 3M.

## 4. User Information

### 4.1 Shelf Life & Storage (prior to application)

Shelf life is 5 years from the manufacturing date. Material should be stored in its original packaging, laying in a horizontal orientation, away from direct sunlight. Heavy objects should not be placed on top of it to avoid damaging the product. Recommended storage conditions are +21°C and 40 – 50% relative humidity. Avoid extreme temperature ranges in storage.

The shelf life as defined above remains an indicative and maximum data, subject to many external and non-controllable factors. It may never be interpreted as warranty.

### 4.2 Application

These are indicative values for 3M™ Window Film products.

Recommended substrate	Glass (as described in EN 15755-1)
Recommended surface	Flat to simple curved
Application method	Suitable for wet application
Application temperature	From +4°C to +45°C
Application guidelines	Use a firm, narrow squeegee e.g. Blue Max 12.7cm. Use both hands to apply consistent, firm pressure across the squeegee blade. Overlap 50% from previous stroke. Remove as much water pass as possible in one pass.
Service temperature	From -40°C to +70°C
Edge sealing	Not necessary
Drying time	Low E films have a strong barrier layer which slows drying time. Water left behind can accumulate and form visible pockets. Once all water is removed, final adhesion is reached after approximately 30 days at +18°C and dry conditions. Please refer to local instructions for details.

### 4.3 Maintenance and Cleaning

Use a cleaning agent designed for high quality glass surfaces. The cleaning agent must be wet and non-abrasive with a pH value between 6 and 8 (neither strongly acidic nor strongly alkaline). Use wet cotton wipes or wet paper towels to clean Thinsulate CC75. Dry microfiber cloths can be used to clean Thinsulate CC75. Never use a wet microfiber cloth.

## 5. Remarks

This bulletin provides technical information only.  
To request additional product information see address below.

### Important Notice

All questions of warranty and liability relating to this product are governed by the terms and conditions of the sale, subject, where applicable, to the prevailing law.

Before using, the user must determine the suitability of the product for its required or intended use, and the user assumes all risk and liability whatsoever in connection therewith.



**Commercial Solutions Division**  
Hermeslaan 7  
1831 Diegem, Belgium  
[www.3mgraphics.com/eu](http://www.3mgraphics.com/eu)

Responsible for this technical bulletin:

3M Deutschland GmbH  
Carl-Schurz-Str. 1  
41453 Neuss, Germany

3M is a trademark of 3M Company. All other trademarks are the property of their respective owners.

The use of trademark signs and brand names in this bulletin is based upon US standards. These standards may vary from country to country outside the USA.

© 3M 2017. All rights reserved.